

DECLARATION OF PERFORMANCE
SKHU_OSB/3_CPR_002

in accordance with Regulation (EU) No 305/2011 of the European Parliament and of the Council of 9 March 2011 laying down harmonized conditions for the marketing of construction products and repealing Council Directive 89/106/EEC

1. Unique identification code of the product-type:

SWISS KRONO OSB/3, 6 – 40mm

2. Intended use:

For non load bearing and load bearing applications
in dry and humid conditions

3. Manufacturer:

SWISS KRONO Kft.
Ipar utca 1,
4800 Vásárosnamény
Hungary
Tel.: +36 45 57 11 31
E-mail: huva.info@swisskrono.com
Web: www.swisskrono.hu

4. Authorised representative:

Not applicable

5. System of AVCP:

System 2+

6. Harmonised standard:

EN 13986:2004+A1:2015

7. Notified body:

WKI – Wilhelm Klauditz Institut für Holzforschung
Bienroder Weg 54 E
38108 Braunschweig
Germany

Nr. 0765

8.Declared performances:

Essential characteristics	Performance						
Thickness range(mm)	6 ≤ 10		> 10 ≤ 18		> 18 ≤ 40		
Bending strength	Technical class OSB/3 according to EN 300						
Modulus of Elasticity	Technical class OSB/3 according to EN 300						
Internal bond	Technical class OSB/3 according to EN 300						
Durability (Swelling in thickness)	Technical class OSB/3 according to EN 300						
Formaldehyde emission	E1 (100% formaldehyde free resin)						
Water vapour permeability (μ)	200 (wet cup) / 300 (dry cup)						
Airborne sound insulation	NPD						
Sound absorption	NPD						
Thermal conductivity (W/(m•K))	0,13						
Strength and stiffness for structural use Thickness range (mm)	6 ≤ 10		> 10 ≤ 18		> 18 ≤ 25		> 25 ≤ 40
Orientation	0°	90°	0°	90°	0°	90°	0° 90°
• Characteristic strength (N/mm²)							
Bending f_m	18,0	9,0	16,4	8,2	14,8	7,4	NPD
Tensile force f_t	9,9	7,2	9,4	7,0	9,0	6,8	NPD
Compression f_c	15,9	12,9	15,4	12,7	14,8	12,4	NPD
Shear perpendicular to the board plane f_v	6,8						NPD
Shear in the board plane f_{tr}	1,0						NPD
• Average resilience (N/mm²)							
Bending E_m	4930	1980	4930	1980	4930	1980	NPD
Tensile force E_t	3800	3000	3800	3000	3800	3000	NPD
Compression E_c	3800	3000	3800	3000	3800	3000	NPD
Shear perpendicular to the board plane G_v	1080						NPD
Shear in the board plane G_{tr}	50						NPD
Mechanical durability							
• Modifying coefficients of strength k_{mod}							
Load duration class:	Service class	Constant	Long	Moderately long	Brief	Very brief	
	1	0,40	0,50	0,70	0,90	1,10	
	2	0,30	0,40	0,55	0,70	0,90	
• Modifying coefficients of deformation k_{def}	1	1,50					
	2	2,25					
Biological durability	1 + 2						
Content of pentachlorophenol (ppm)	< 5						
Racking resistance	NPD						
Embedment strength	NPD						

Point 8. continuation

Essential characteristics	Performance		
Density (kg/m ³)	≥ 600		
Reaction to fire / Application	Class		
	Min. Thickness (mm)	Class (without flooring) ^g	Class (flooring) ^h
Without an air gap behind the wood-based panel ^{a b e f}	9	D-s2, d0	D _{fl} , s1
With a closed or an open air gap not more than 22mm behind the wood-based panel ^{c e f}	9	D-s2, d2	-
With a closed air gap behind the wood-based panel ^{d e f}	15	D-s2, d0	D _{fl} , s1
With an open air gap behind the wood-based panel ^{d e f}	18	D-s2, d0	D _{fl} , s1
Any ^{e f}	3	E	E _{fl}

^a Mounted without an air gap directly against class A1 or A2-s1, d0 products with minimum density 10 kg/m³ or at least class D-s2, d2 products with minimum density 400 kg/m³
^b A substrate of cellulose insulation material of at least class E may be included if mounted directly against the wood-based panel, but not for floorings
^c Mounted with an air gap behind. The reverse face of the cavity shall be at least class A2-s1, d0 products with minimum density 10 kg/m³
^d Mounted with an air gap behind. The reverse face of the cavity shall be at least class D-s2, d2 products with minimum density 400 kg/m³
^e Veneered, phenol- and melamine-faced panels are included for class excl. floorings
^f A vapour barrier with a thickness up to 0,4 mm and a mass up to 200 g/m² can be mounted in between the wood-based panel and a substrate if there are no air gaps in between
^g Class as provided for in Table 1 of the Annex to Decision 2000/147/EC
^h Class as provided for in Table 2 of the Annex to Decision 2000/147/EC

NPD: No Performance Determined

The performance of the product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:



Szilárd Kázmér
Managing director
(Technical and production leader)



Tivadar Okszana
Quality Manager